



# STARDEK WATERBORNE ACRYLIC SDII CLEAR SEALER

Technical Report

VOC Compliant

### Directions For Use:

STARDEK Water Based Clear Top Glaze is non-yellowing. It is designed to protect newly applied Waterborne STARDECK Concrete Sealer Surfaces. **DO NOT THIN.** STARDEK Clear Top Glaze resists fading, cracking, peeling, and mildew. Excellent for protecting newly applied designs on driveways, etc. Damp, soiled or inclined surfaces may result in a degree of slipperiness, user must determine if a non-skid additive should be added to the Base Coat of STARDEK Concrete Sealer before the application of the Clear Coating.

### Surface Preparation:

**Older Concrete** – Older concrete surfaces must be thoroughly cleaned.

**Mildew** – Remove mildew & fungus by applying one (1) part bleach to two (2) parts water, scrub and rinse thoroughly with clean water

**Oil Spots** – Remove by applying an industrial cleaner and wire brushing. Repeat until oil is removed

**Rust Spots** – Remove by applying a rust spot remover.

**When possible, pressure clean using 2500 to 3000 psi is recommended.**

### Application:

Brush or roll. When applying with a short nap roller (3/8" Nap) Waterborne. DO NOT APPLY EXCESSIVE PRESSURE ON THE ROLLER. Roll with light to medium pressure. Apply Top Glaze evenly and do not leave puddles or roller marks. One (1) coat is required. DO NOT apply to areas where standing water is evident. Clean tools with warm water and soap.

### Coverage:

Average 200-300 sq. ft. per gallon. Surface will be tack free in hour, ready for foot traffic in two hours and vehicle traffic in 72 hours. Low temperatures and high humidity will prolong drying time.

**Do Not Apply below 50 degrees!  
Do Not Apply to a damp surface!**

**KEEP FROM FREEZING!**

### Technical Data:

**Generic Type** – Waterborne Acrylic

**Color** – Clear

**Sheen** – Gloss

**% Solids by Weight** – 27.67%

**% Solids by Volume** – 25.50%

**Recommended Coverage:**

Average 300-500 sq. ft per gallon on porous surfaces

**% Vehicle Solids by Weight** – 27.27%

**% Volatile by Weight** – 72.33%

**Viscosity #2 Zahn** – 16-17 Sec.

**VOC** – 188 grams/liter

1.57 lbs/gallon

**Weight/Gallon** – 8.54 lbs.

**Flash Point** – N/A

**Dry Time** - 70°F, 50% R.H.

Touch – 1 hour (Depending on Weather)

Recoat – 2 hours (High humidity and/or low temperatures will affect dry time)

Apply above 50°F

**Reduction Solvent** – Clean water

**Clean Up** – Warm soapy water

KEEP FROM FREEZING

**THE CHOICE OF  
PROFESSIONALS...**

STARDEK® mfg. by:  
Color-Crown Corporation  
928 Sligh Ave.  
Seffner, FL 33584  
(800) 282-1599 □ Fax(813) 655-8830